DESCRIPTION

POLISHING COMPOSITION AND RINSING COMPOSITION

5   TECHNICAL FIELD

The present invention relates to a polishing composition and a rinsing composition, and more particularly, it relates to a polishing composition used for polishing silicon wafers and a rinsing composition used for rinsing silicon wafers.

10

BACKGROUND ART

In processes for semiconductor device production, silicon wafers are mechanically and chemically polished using a polishing composition. Thereafter, the polished silicon
15 wafers are generally rinsed using water or a rinsing composition such that the silicon wafers are protected from remaining silicon dioxide and metal impurities contained in the polishing composition.

20   A conventional polishing composition disclosed in Japanese Laid-Open Patent Publication No. 63-272460 contains at least one chelating agent such as ethylenediaminetetraacetic acid (EDTA), and a high molecular ion having a molecular weight of 5000 or more such as
25 polyacrylic acid, in addition to water and particulate amorphous silica. Another conventional polishing composition disclosed in Japanese Laid-Open Patent Publication No. 2001-77063 contains polishing particles, amines such as piperazine, and a chelating agent such as EDTA.

30

These conventional polishing compositions prevent the silicon wafers from being contaminated by metal impurities contained in the polishing compositions by virtue of the chelating agent that coordinates with a metal element to form
35 a stable complex ion. The chelating agents contained in the

- 1 -

conventional polishing compositions, however, do not have a very high capability for capturing metal impurities. Therefore, in the case where semiconductor devices are fabricated from silicon wafers polished using the prior art

5   polishing compositions, poor conditions for semiconductors are often caused due to short circuits or leaks. The silicon wafer contamination caused by metal impurities means not only adhesion of metal impurities on the surface of the silicon wafer but also diffusion of metal impurities in the inside of

10   the silicon wafer.

DISCLOSURE OF THE INVENTION

It is an objective of the present invention to provide a polishing composition and a rinsing composition, both of which

15   compositions can effectively suppress wafer contamination caused by metal impurities.

In order to attain the above objective, the present invention provides the following polishing composition for use

20   in polishing a silicon wafer. The polishing composition includes a chelating agent, an alkali compound, silicon dioxide and water. The chelating agent is an acid represented by the following chemical formula:

$$\begin{array}{c} R^8 \\ \diagdown \\ \diagup N - (Y^2 - N)_n - Y^3 - N \diagup^{R^{10}} \\ R^9 \qquad \; | \qquad \diagdown R^{11} \\ R^{12} \end{array}$$

25   or a salt thereof. In the chemical formula, each of Y^2 and Y^3 represents an alkylene group, n is an integer of 0 to 4, each of 4+n substituents represented by R^8 to R^{12} is an alkyl group and at least four of the alkyl groups have a phosphonic acid group.

30

Further, the present invention provides the following process for polishing a silicon wafer. The process includes

- 2 -

the step of preparing a polishing composition and polishing
the silicon wafer surface by using the polishing composition.
The above polishing composition includes a chelating agent, an
alkali compound, silicon dioxide and water. The chelating

5 agent is an acid represented by the following chemical
formula:

$$\underset{R^9}{\overset{R^8}{\diagdown}}N-(Y^2-\underset{\underset{R^{12}}{|}}{N})_n-Y^3-N\underset{R^{11}}{\overset{R^{10}}{\diagup}}$$

or a salt thereof. In the chemical formula, each of Y^2 and Y^3
represents an alkylene group, n is an integer of 0 to 4, each

10 of 4+n substituents represented by R^8 to R^{12} is an alkyl group
and at least four of the alkyl groups have a phosphonic acid
group.

Moreover, the present invention provides the following

15 rinsing composition for use in rinsing a silicon wafer. The
rinsing composition includes a chelating agent, an alkali
compound and water. The chelating agent is an acid
represented by the following chemical formula:

$$\underset{R^9}{\overset{R^8}{\diagdown}}N-(Y^2-\underset{\underset{R^{12}}{|}}{N})_n-Y^3-N\underset{R^{11}}{\overset{R^{10}}{\diagup}}$$

20 or a salt thereof. In the chemical formula, each of Y^2 and Y^3
represents an alkylene group, n is an integer of 0 to 4, each
of 4+n substituents represented by R^8 to R^{12} is an alkyl group
and at least four of the alkyl groups have a phosphonic acid
group.

25

In addition, the present invention provides the following
process for rinsing a silicon wafer. The process includes the
step of preparing a rinsing composition and rinsing the
silicon wafer surface by using the rinsing composition. The

above rinsing composition includes a chelating agent, an alkali compound and water. The chelating agent is an acid represented by the following chemical formula:

$$R^8 \diagdown N - (Y^2 - N)_n - Y^3 - N \diagup R^{10}$$
$$R^9 \diagup \quad\quad R^{12} \quad\quad R^{11} \diagdown$$

5   or a salt thereof. In the chemical formula, each of Y^2 and Y^3 represents an alkylene group, n is an integer of 0 to 4, each of 4+n substituents represented by R^8 to R^{12} is an alkyl group and at least four of the alkyl groups have a phosphonic acid group.

10

BRIEF DESCRIPTION OF THE DRAWING

       Fig. 1 is a perspective view showing a polishing apparatus used in polishing with the polishing composition and in rinsing with the rinsing composition.

15

BEST MODE FOR CARRYING OUT THE INVENTION

       Hereinafter, one embodiment of the present invention will be described.

20   First, the work process for silicon wafers is described. In the first place, a silicon single crystal ingot is sliced to prepare silicon wafers. The silicon wafers are made to have a predetermined shape by lapping. Next, each of the silicon wafers is etched in order to remove the silicon wafer
25   surface layer deteriorated by the lapping. After the etching, the edge and the surface of each silicon wafer are polished successively and then the silicon wafer is rinsed.

       The polishing composition according to this embodiment
30   includes a chelating agent, an alkali compound, silicon dioxide and water, and is used in polishing the silicon wafer surface. The rinsing composition of this embodiment includes

a chelating agent, an alkali compound and water, and is used
in rinsing the silicon wafer surface.

The chelating agent is an acid represented by the formula
1:

$$R^8\!\!\diagdown \atop R^9\!\!\diagup N - (Y^2 - \underset{R^{12}}{N})_n - Y^3 - N\!\!\diagup^{R^{10}}_{\diagdown R^{11}}$$

or a salt thereof, and the chelating agent is coordinated to a
metal element to form a stable complex ion. The chelating
agent contained in the polishing composition plays a role in
capturing metal impurities contained in the polishing
composition, and the chelating agent contained in the rinsing
composition plays a role in capturing metal impurities
remaining in silicon wafers.

Each of Y^2 and Y^3 in the chemical formula 1 represents an
alkylene group. The alkylene group may be linear or branched.
The alkylene group is preferably a lower alkylene group having
1 to 4 carbon atoms. The chelating agent in which the
alkylene group is a lower alkylene group has a high capability
for capturing metal impurities. Specific examples of the
lower alkylene group may include a methylene group, an
ethylene group, a propylene group, a methylmethylene group, a
methylethylene group, an ethylmethylene group, a butylene
group, a methylpropylene group and an ethylethylene group.
n in the chemical formula 1 is an integer of 0 to 4, and
preferably an integer of 0 to 2. The chelating agent in which
n is an integer of 0 to 2 is easily synthesized.

Each of R^8 to R^{12} in the chemical formula 1 represents an
alkyl group. The alkyl group may be linear or branched. The
alkyl group is preferably a lower alkyl group having 1 to 4
carbon atoms. The chelating agent in which the alkyl group is

- 5 -

a lower alkyl group has a high capability for capturing metal impurities. Specific examples of the lower alkyl group may include a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, an isobutyl group, a sec-
5 butyl group and a tert-butyl group.

Among 4+n alkyl groups represented by R^8 to R^{12}, at least four alkyl groups, preferably all the 4+n alkyl groups have a phosphonic acid group. The chelating agent in which all the
10 4+n alkyl groups have a phosphonic acid group have a high capability of capturing metal impurities. Each alkyl group preferably has from 1 to 2 phosphonic acid groups, more preferably one phosphonic acid group.

15 From the viewpoint of having a high capability of capturing metal impurities, preferable examples of the chelating agent may include ethylenediaminetetraethylenephosphonic acid, ethylenediaminetetramethylenephosphonic acid (EDTP),
20 diethylenetriaminepentaethylenephosphonic acid, diethylenetriaminepentamethylenephosphonic acid (DTPP), triethylenetetraminehexaethylenephosphonic acid, triethylenetetraminehexamethylenephosphonic acid (TTHP), propanediaminetetraethylenephosphonic acid and
25 propanediaminetetramethylenephosphonic acid, and their ammonium salts, potassium salts, sodium salts and lithium salts. From the viewpoint of having a particularly high capability for capturing metal impurities, more preferable examples of the chelating agent may include
30 ethylenediaminetetraethylenephosphonic acid, EDTP, ammonium ethylenediaminetetramethylenephosphonate, potassium ethylenediaminetetramethylenephosphonate (EDTPP), sodium ethylenediaminetetramethylenephosphonate, lithium ethylenediaminetetramethylenephosphonate,
35 diethylenetriaminepentaethylenephosphonic acid, DTPP, ammonium

- 6 -

diethylenetriaminepentamethylenephosphonate, potassium
diethylenetriaminepentamethylenephosphonate (DTPPP), sodium
diethylenetriaminepentamethylenephosphonate, lithium
diethylenetriaminepentamethylenephosphonate,

5   triethylenetetraminehexaethylenephosphonic acid, TTHP,
ammonium triethylenetetraminehexamethylenephosphonate,
potassium triethylenetetraminehexamethylenephosphonate (TTHPP),
sodium triethylenetetraminehexamethylenephosphonate, lithium
triethylenetetraminehexamethylenephosphonate,

10 propanediaminetetraethylenephosphonic acid,
propanediaminetetramethylenephosphonic acid, ammonium
propanediaminetetramethylenephosphonate, potassium
propanediaminetetramethylenephosphonate, sodium
propanediaminetetramethylenephosphonate and lithium

15 propanediaminetetramethylenephosphonate. Each of the
polishing composition and the rinsing composition may contain
one kind of the chelating agent or two or more kinds of the
chelating agents.

20   In the polishing composition and the rinsing composition,
the content of the chelating agent is preferably from 0.001 to
6% by weight, more preferably 0.005 to 3% by weight, most
preferably 0.01 to 1% by weight. A polishing composition and
a rinsing composition having too low of a content of the

25 chelating agent do not satisfactorily suppress silicon wafer
contamination caused by metal impurities. A polishing
composition and a rinsing composition having too much of a
content of the chelating agent are easily gelled and are
uneconomical.

30

     The above-described alkali compound is contained in the
polishing composition and the rinsing composition for
maintaining alkaline conditions for the polishing composition
and the rinsing composition. The alkali compound contained in

35 the polishing composition plays a role in accelerating

- 7 -

polishing of the silicon wafer surface by chemical actions such as corrosion, etching and oxidation.

Specific examples of the alkali compound may include
5   inorganic alkali compounds such as potassium hydroxide (PHA), sodium hydroxide (NHA), potassium hydrogen carbonate (PCAH), potassium carbonate (PCA), sodium hydrogen carbonate (NCAH) and sodium carbonate (NCA); ammonia (AM); ammonium salts such as tetramethyl ammonium hydroxide (TMAH), ammonium hydrogen
10 carbonate (ACAH) and ammonium carbonate (ACA); and amines such as methylamine (MA), dimethylamine (DMA), trimethylamine (TMA), ethylamine (EA), diethylamine (DEA), triethylamine (TEA), ethylenediamine (EDA), monoethanolamine (MEA), N-(β-aminoethyl)ethanolamine (AEEA), hexamethylenediamine (HMDA),
15 diethylenetriamine (DETA), triethylenetetramine (TETA), piperazine anhydride (PIZ), piperazine hexahydrate, 1-(2-aminoethyl)piperazine (AEPIZ) and N-methylpiperazine (MPIZ). Because of having low amine odor, preferable examples of the alkali compound may include PHA, NHA, PCAH, PCA, NCAH, NCA, AM,
20 TMAH, ACAH, ACA, EDA, MEA, AEEA, HMDA, DETA, TETA, PIZ, piperazine hexahydrate, AEPIZ and MPIZ. Because the alkali compound does not inhibit the functions of the chelating agent in addition to having a low amine odor, more preferable examples thereof may include PHA, NHA, PCAH, PCA, NCAH, NCA,
25 AM, TMAH, ACAH, ACA, PIZ, piperazine hexahydrate, AEPIZ and MPIZ. The polishing composition and the rinsing composition may contain one kind of the alkali compounds or two or more kinds thereof.

30   In the case where the alkali compound is PHA, NHA, TMAH, ACAH, ACA, PCAH, PCA, NCAH, NCA, AM, MA, DMA, TMA, EA, DEA, TEA, EDA, MEA, AEEA, HMDA, DETA, or TETA, the polishing composition and the rinsing composition have a content of the alkali compounds of preferably from 0.1 to 6% by weight, more
35 preferably 0.5 to 5% by weight, and most preferably 1 to 4% by

- 8 -

weight. In the case where the alkali compound is PIZ, AEPIZ, or MPIZ, they have a content of the alkali compounds of preferably from 0.1 to 10% by weight, more preferably 1 to 9% by weight, most preferably 3 to 8% by weight, and in the case where the alkali compound is piperazine hexahydrate, they have a content of the alkali compounds of preferably from 0.1 to 20% by weight, more preferably 2 to 18% by weight, and most preferably 5 to 16% by weight. A polishing composition having too low of a content of the alkali compound does not have a very high polishing rate. A polishing composition and a rinsing composition having too much of a content of the alkali compound are easily gelled and are uneconomical as well as easily cause roughness on the silicon wafer surface.

The above-described silicon dioxide plays a role in mechanically polishing the silicon wafer surface. Examples of the silicon dioxide may include colloidal silica, fumed silica, precipitated silica and the like. Because of contributing to improvement in the polishing accuracy, colloidal silica is preferred as the silicon dioxide.

In the case where the silicon dioxide is colloidal silica, the silicon dioxide has an average particle diameter D_{SA}, as determined from the specific surface area measured by a method of measuring specific surface area of powder with gas adsorption (BET method), of preferably from 5 to 300 nm, more preferably 5 to 200 nm, most preferably 5 to 120 nm, and in the case where the silicon dioxide is fumed silica or precipitated silica, the silicon dioxide has an average particle diameter D_{SA} of preferably from 10 to 300 nm, more preferably 10 to 200 nm, and most preferably 10 to 150 nm. In the case where the silicon dioxide is colloidal silica, the silicon dioxide has an average particle diameter D_{N4}, as calculated from laser scattering, of preferably from 5 to 300 nm, more preferably 10 to 200 nm, and most preferably 15 to

150 nm, and in the case where the silicon dioxide is fumed
silica or precipitated silica, the silicon dioxide has an
average particle diameter D_{N4} of preferably from 30 to 500 nm,
more preferably 40 to 400 nm, and most preferably 50 to 300 nm.
5   A polishing composition containing silicon dioxide having an
average particle diameter D_{SA} or D_{N4} that is too small does not
have a very high polishing rate. A polishing composition
containing silicon dioxide having an average particle diameter
D_{SA} or D_{N4} that is too large easily roughens the silicon wafer
10 surface or easily causes defects such as scratches, and haze
on the silicon wafer surface

    The silicon dioxide usually contains metal elements such
as calcium and magnesium, as well as transition metal elements
15 such as iron, nickel and copper, as metal impurities. In the
20% by weight of silicon dioxide aqueous solution, the total
content of elements of iron, nickel, copper and calcium is
preferably not more than 300 ppm, more preferably not more
than 100 ppm, and most preferably not more than 0.3 ppm. When
20 the total content is too much, silicon wafers are easily
contaminated by metal impurities derived from the silicon
dioxide, contained in the polishing composition and a large
amount of the chelating agent needs to be contained in the
polishing composition, so that the cost is increased.
25

    The polishing composition has a silicon dioxide content
of preferably 1 to 50% by weight, more preferably 5 to 50% by
weight, and most preferably 10 to 50% by weight. A polishing
composition having too low of a silicon dioxide content does
30 not have a higher polishing rate, while a polishing
composition having too much of a silicon dioxide content is
easily gelled.

    The above-described water plays a role as a medium
35 capable of dispersing the silicon dioxide and dissolving the

chelating agent and the alkali compound. The water, as much
as possible, preferably does not contain impurities.
Preferable examples of the water may include ion exchange
water, pure water, ultra-pure water and distilled water.

5

The polishing composition and the rinsing composition
preferably have a pH of from 8 to 12, and more preferably 10
to 12. A polishing composition having too low of a pH does
not have very high polishing rate. A polishing composition

10   and rinsing composition having too high of a pH are easily
gelled. It is preferred that the pH of the polishing
composition be almost the same as the pH of the rinsing
composition. When the pH of the polishing composition is
greatly different from the pH of the rinsing composition,

15   during rinsing, the polishing composition remaining on the
silicon wafer surface and polishing pad is gelled or roughness
is generated on the silicon wafer surface.

With regard to the polishing composition and the rinsing

20   composition, the polishing composition is prepared by mixing
components other than water, namely the chelating agent, the
alkali compound and silicon dioxide with water, and the
rinsing composition is prepared by mixing components other
than water, namely the chelating agent and alkali compound

25   with water. In the mixing process, a blade type stirrer or an
ultrasonic dispersion machine may be used.

Next, a polishing apparatus 11 as shown in Fig. 1 will be
described.

30

The polishing apparatus 11 is equipped with a disk-like
rotary platen 12 having a polishing pad 14 adhered on the
upper surface thereof. The rotary platen 12 is rotatably
provided to a first shaft 13 capable of rotating in the

35   direction shown by the arrow 13a in Fig. 1 so as to rotate

- 11 -

integrally with the first shaft 13. Above the rotary platen
12, at least one wafer holder 15 is provided. The wafer
holder 15 is rotatably provided to a second shaft 16 capable
of rotating in the direction shown by the arrow 16a in Fig. 1
5   so as to rotate integrally with the second shaft 16. On the
bottom surface of the wafer holder 15, a wafer holding plate
19 having four wafer holding holes 18 is removably equipped
through a ceramic plate 17 and an unillustrated urethane sheet.
The polishing apparatus 11 is further equipped with a
10   polishing composition feeder 21 and an unillustrated rinsing
composition feeder. The polishing composition feeder 21
discharges the polishing composition through a nozzle 21a and
the rinsing composition feeder discharges the rinsing
composition through an unillustrated nozzle. Any one of the
15   polishing composition feeder 21 and the rinsing composition
feeder is disposed above the rotary platen 12. One feeder
disposed above the rotary platen 12 can be replaced with the
other feeder, which is not disposed above the rotary platen 12.

20   When silicon wafers are polished, the polishing
composition feeder 21 is disposed above the rotary platen 12,
as shown in Fig. 1. The silicon wafers for polishing are
sucked into the wafer holding holes 18 and retained in the
wafer holder 15. Firstly, the rotation of the wafer holder 15
25   and the rotary platen 12 is started, and the polishing
composition is discharged from the polishing composition
feeder 21 and fed to the polishing pad 14. Thereafter, the
wafer holder 15 is moved toward the rotary platen 12 so that
each of the silicon wafers is pressed on the polishing pad 14.
30   Thus, the silicon wafer surface, which is in contact with the
polishing pad 14, is polished.

        Following the polishing, when the polished silicon wafers
are rinsed, the rinsing composition feeder is disposed above
35   the rotary platen 12 in place of the polishing composition

feeder 21. The operation conditions for the polishing apparatus 11 are changed to the setting for rinsing from that for polishing. Thereafter, the rinsing composition is discharged from the rinsing composition feeder and thereby the rinsing composition is fed to the polishing pad 14. Thus, the silicon wafer surface, which is in contact with the polishing pad 14, is rinsed.

The polishing process for the silicon wafer surface is preferably carried out by division into a plurality of steps. For example, the silicon wafer surface may be polished in three steps including a first step of rough polishing, a second step of precise polishing, and a third step of finishing polishing. In this case, the silicon wafer is preferably rinsed every time a step is completed.

The embodiment has the following advantages.

The chelating agent contained in the polishing composition and the rinsing composition according to this embodiment has a higher capability for capturing metal impurities as compared with conventional chelating agents such as EDTA. In addition, the chelating agent with metal impurities captured electrostatically repels the silicon wafer surface showing a negative at a zeta potential. Accordingly, contamination of silicon wafer caused by metal impurities is effectively suppressed.

The polishing and rinsing of the silicon wafer are continuously carried out by the same polishing apparatus 11 while the silicon wafer is held in the wafer holder 15. Therefore, etching and stains on the silicon wafer surface caused by contacting the silicon wafer to the polishing composition for a long time after the completion of the polishing, are suppressed. Further, caking of foreign

- 13 -

substances (particles) such as silicon dioxide, on the silicon wafer surface caused by drying is also suppressed and thereby LPD (Light Point Defect), which is one kind of surface defect in silicon wafers, is decreased. Furthermore, the labor hours and cost for the polishing and rinsing is decreased.

The above embodiment may be changed in the following manner.

The polishing composition may be prepared by diluting a stock solution containing a chelating agent, an alkali compound and silicon dioxide in a high concentration with water at the time of using the polishing composition. In this case, the storage and conveyance of the polishing composition is easy before the use thereof. As the polishing composition, the stock solution for the polishing composition is preferably diluted with water in a volume of from 1 to 50 times based on the volume of the stock solution, more preferably 1 to 40 times, and most preferably 1 to 20 times.

The rinsing composition may be prepared by diluting a stock solution containing a chelating agent and an alkali compound in a high concentration with water at the time of using the rinsing composition. In this case, the storage and conveyance of the rinsing composition is easy before the use thereof. As the rinsing composition, the stock solution for the rinsing composition is preferably diluted with water in a volume of from 1 to 100 times based on the volume of the stock solution, more preferably 1 to 80 times, and most preferably 1 to 40 times.

In place of the polishing apparatus 11 shown in Fig. 1, the silicon wafer polishing and rinsing may be carried out using a double-sided polishing apparatus capable of polishing both surfaces of a silicon wafer simultaneously.

- 14 -

After the completion of the polishing and rinsing, the silicon wafer surface may be subjected to scrubbing washing with, for example, a polyvinyl alcohol made sponge using a washing water such as pure water and ultra-pure water.

The polishing composition and the rinsing composition may contain conventionally known additives such as a surfactant and an antiseptic agent, as necessary. For example, the polishing composition and the rinsing composition may contain hydrogen peroxide. In this case, an oxidation film is formed on the silicon wafer surface by hydrogen peroxide and thereby particles do not adhere on the silicon wafer surface directly so that LPD is improved.

Before rinsing the polished silicon wafer surface, the wafer holder 15 may be kept away from the rotary platen 12 and thereby the silicon wafer may be detached once from the polishing pad 14. Then, the feeding of the rinsing composition to the polishing pad 14 may be started, the silicon wafer may be placed in contact with the polishing pad 14 again and rinsing thereof may be started.

Next, the present invention is further described in more detail with reference to the following Examples and Comparative Examples.

Examples 1 to 14 and Comparative Examples 1 to 9

In each of Examples 1 to 14 and Comparative Examples 1 to 9, a polishing composition stock solution was prepared by mixing silicon dioxide, a chelating agent, an alkali compound and water. The silicon dioxide contained in each polishing composition stock solution is colloidal silica, and each polishing composition stock solution contains colloidal silica in an amount of 20% by weight. With regard to the chelating

agent and the alkali compound contained in each polishing
composition stock solution, the kinds and contents thereof are
shown in Table 1. Furthermore, in a 20% by weight colloidal
silica aqueous solution, the total content of elements of iron,
nickel, copper and calcium is not more than 20 ppb. The
colloidal silica has an average particle diameter D_{SA}, as
measured by a FlowSorbII2300 manufactured by Micromeritics Co.,
of 35 nm and has an average particle diameter D_{N4}, as measured
by an N4 Plus Submicron Particle Sizer manufactured by Beckman
Coulter, Inc., of 70 nm. In each of Examples 1 to 14, the
polishing composition stock solution has a pH of from 10 to 12.
Each polishing composition stock solution was diluted to 20
times with ultra pure water to prepare a polishing composition,
and using the polishing composition, the silicon wafer surface
was polished under the following polishing conditions 1.

Polishing conditions 1
        Polishing apparatus: Single-sided polishing machine SPM-
15 (equipped with four wafer holders each capable of holding
four wafers) manufactured by Fujikoshi Machinery Corp.,
        Object to be polished: 6 inch silicon wafer (p type,
Crystal orientation <100>, Resistivity of from 1 to 10 Ω·cm)
        Load: 31.5 kPa
        Number of revolutions of platen: 58 rpm
        Number of revolutions of wafer holder: 120 rpm
        Polishing pad: Non-woven fabric Suba600 manufactured by
Rodel Nitta Corp.
        Feed rate of polishing composition: 8000 mL/min (use with
circulation)
        Polishing time: 15 minutes
        Temperature of polishing composition: 23°C

(1) Content of metal impurities on a silicon wafer surface
        After polishing, a silicon wafer was subjected to scrub
cleaning with pure water. Subsequently, the naturally

- 16 -

oxidized film of the silicon wafer surface was subjected to
gas phase decomposition with hydrofluoric acid vapor and then
recovered by droplets containing hydrofluoric acid and aqueous
hydrogen peroxide. The metal impurities contained in the
5 recovered solution were subjected to quantitative analysis by
inductively coupled plasma mass spectrometric analysis (ICP-
MS). The amount of the metal impurities was evaluated by four
classes, that is, an amount of less than 1×10^9 atms/cm^2 is
represented by a ◎, an amount of not less than 1×10^9
10 atms/cm^2 and less than 3×10^9 atms/cm^2 is represented by a ○,
an amount of not less than 3×10^9 atms/cm^2 and less than $1 \times$
10^{10} atms/cm^2 is represented by a △, and an amount of not less
than 1×10^{10} atms/cm^2 is represented by a ✕. The results are
shown in Table 1.
15

(2) Content of metal impurities present in the inside of a
silicon wafer
       Using a hydrochloric acid-hydrogen peroxide aqueous
solution (SC-2) containing a 36% hydrochloric acid solution, a
20 31% hydrogen peroxide solution and pure water in a volume
ratio of 1:1:6, a polished silicon wafer was washed and then
treated with heat at 200°C for 48 hours, and thereby metal
impurities present in the inside of the silicon wafer were
transferred to the silicon wafer surface. Thereafter, in
25 accordance with the method as described in (1) above, the
amount of these metal impurities was measured and evaluated.
The results are shown in Table 1.

(3) Polishing rate
30   The polishing rate was calculated from the difference
between the thickness of the center part of a silicon wafer
before polishing and that after polishing. The difference is
an average of the differences of the thicknesses, which are
measured by a dial gauge, on four silicon wafers
35 simultaneously polished with holding different wafer holders

- 17 -

respectively. The polishing rate was evaluated by four
classes, that is, a polishing rate of not lower than 1 μm/min
is represented by a ◎, a polishing rate of not lower than 0.8
μm/min and lower than 1 μm/min is represented by a ○, a

5 polishing rate of not lower than 0.5 μm/min and lower than 0.8
μm/min is represented by a △, and a polishing rate of lower
than 0.5 μm/min is represented by a ×. The results are shown
in Table 1.

10 Table 1

	Chelating agent		Alkali compound						Metal impurities								
									silicon wafer surface				silicon wafer inside				
	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	Fe	Ni	Cu	Ca	Fe	Ni	Cu	Ca	Polishing rate
Ex. 1	DTPPP	0.1	PHA	1.5	-		-		○	○	◎	◎	◎	○	◎	◎	△
Ex. 2	DTPPP	0.1	NCA	1.5	-		-		○	○	◎	◎	◎	○	◎	◎	△
Ex. 3	EDTP	0.1	TMAH	2	-		-		○	○	○	◎	◎	○	○	◎	○
Ex. 4	EDTPP	0.1	TMAH	2	-		-		○	○	○	◎	◎	○	○	◎	○
Ex. 5	DTPP	0.1	TMAH	2	-		-		○	○	◎	◎	◎	○	◎	◎	○
Ex. 6	DTPPP	0.01	TMAH	2	-		-		○	○	○	○	◎	○	○	○	○
Ex. 7	DTPPP	0.1	TMAH	2	-		-		○	○	◎	◎	◎	○	◎	◎	○
Ex. 8	DTPPP	1	TMAH	2	-		-		○	◎	◎	◎	◎	◎	◎	◎	○
Ex. 9	TTHP	0.1	TMAH	2	-		-		○	◎	◎	◎	◎	◎	◎	◎	○
Ex. 10	TTHPP	0.1	TMAH	2	-		-		○	◎	◎	◎	◎	◎	◎	◎	○
Ex. 11	DTPPP	0.1	PIZ	6	-		-		○	○	◎	◎	◎	○	◎	◎	◎
Ex. 12	DTPPP	0.1	PIZ	6	TMAH	1	-		○	○	◎	◎	◎	○	◎	◎	◎
Ex. 13	DTPPP	0.1	PHA	0.5	TMAH	2	-		○	○	◎	◎	◎	○	◎	◎	○
Ex. 14	DTPPP	0.1	PIZ	6	PHA	0.5	TMAH	1	○	○	◎	◎	◎	○	◎	◎	◎
C. Ex. 1	-		EDA	3	-		-		×	×	×	×	×	×	×	×	◎
C. Ex. 2	-		PHA	1.5	-		-		×	×	×	×	×	×	×	×	△
C. Ex. 3	-		NCA	1.5	-		-		×	×	×	×	×	×	×	×	△
C. Ex. 4	-		TMAH	2	-		-		×	×	×	×	×	×	×	×	○
C. Ex. 5	EDTA	0.1	TMAH	2	-		-		△	△	△	△	△	△	△	△	○
C. Ex. 6	DTPA	0.1	TMAH	2	-		-		△	○	○	△	△	○	○	△	○
C. Ex. 7	NTA	0.1	TMAH	2	-		-		×	×	×	×	×	×	×	×	○
C. Ex. 8	HIDA	0.1	TMAH	2	-		-		×	×	×	×	×	×	×	×	○
C. Ex. 9	-		PIZ	6	-		-		×	×	×	×	×	×	×	×	◎

In Table 1, DTPA represents diethylenetriaminepentaacetic

- 18 -

acid, NTA represents nitrilotriacetic acid, and HIDA represents hydroxyethyliminodiacetic acid.

As is clear from Table 1, in each of Examples 1 to 14,
5   both of the silicon wafer surfaces and the silicon wafer inside have good evaluations for metal impurities and further, in each of Examples 3 to 14, the evaluation of the polishing rate is also good. However, in each of Comparative Examples 1 to 9, both of the silicon wafer surfaces and the silicon wafer
10   inside do not have good evaluations for metal impurities. This is presumed to be due to the fact that the polishing composition in each of Comparative Examples 1 to 9 does not contain a specific chelating agent.

15   Examples 15 to 28 and Comparative Examples 10 to 18
        In each of Examples 15 to 28 and Comparative Examples 10 to 18, a rinsing composition stock solution was prepared by mixing a chelating agent, an alkali compound and water. The kinds and contents of the chelating agent and the alkali
20   compound contained in each rinsing composition stock solution are shown in Table 2. In each of Examples 15 to 28, the rinsing composition stock solution had a pH of from 10 to 12. Each rinsing composition stock solution was diluted to 20 times with ultra pure water to prepare a rinsing composition.
25   Using the rinsing composition, the silicon wafer surface polished in the above-described polishing conditions 1 was rinsed under the following rinsing conditions 1. It should be noted that in the following rinsing conditions 1, the description of the same items as those in polishing conditions
30   1 is omitted.

Rinsing conditions 1
        Object to be rinsed: 6 inch silicon wafer polished under the polishing conditions 1 using the polishing composition of
35   Comparative Example 4

Load: 2 kPa

Number of revolutions of platen: 30 rpm

Number of revolutions of wafer holder: 62 rpm

Feed rate of rinsing composition: 8000 mL/min (no
circulation)

Rinsing time: 1 minute

Temperature of rinsing composition: 20°C

The content of metal impurities present on the silicon
wafer surface after the rinsing was measured and evaluated in
accordance with the method as described in (1). The results
are shown in Table 2.

Table 2

	Chelating agent		Alkali compound						Metal impurities silicon wafer surface			
	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	Fe	Ni	Cu	Ca
Ex. 15	DTPPP	0.1	PHA	1.5	-		-		O	O	◎	◎
Ex. 16	DTPPP	0.1	NCA	1.5	-		-		O	O	◎	◎
Ex. 17	EDTP	0.1	TMAH	2	-		-		O	O	O	◎
Ex. 18	EDTPP	0.1	TMAH	2	-		-		O	O	O	◎
Ex. 19	DTPP	0.1	TMAH	2	-		-		O	O	◎	◎
Ex. 20	DTPPP	0.01	TMAH	2	-		-		O	O	O	O
Ex. 21	DTPPP	0.1	TMAH	2	-		-		O	O	◎	◎
Ex. 22	DTPPP	1	TMAH	2	-		-		O	◎	◎	◎
Ex. 23	TTHPP	0.1	TMAH	2	-		-		O	◎	◎	◎
Ex. 24	TTHP	0.1	TMAH	2	-		-		O	◎	◎	◎
Ex. 25	DTPPP	0.1	PIZ	6	-		-		O	O	◎	◎
Ex. 26	DTPPP	0.1	PIZ	6	TMAH	1	-		O	O	◎	◎
Ex. 27	DTPPP	0.1	PHA	0.5	TMAH	2	-		O	O	◎	◎
Ex. 28	DTPPP	0.1	PIZ	6	PHA	0.5	TMAH	1	O	O	◎	◎
C. Ex. 10	-		EDA	3	-		-		×	×	×	×
C. Ex. 11	-		PHA	1.5	-		-		×	×	×	×
C. Ex. 12	-		NCA	1.5	-		-		×	×	×	×
C. Ex. 13	-		TMAH	2	-		-		×	×	×	×
C. Ex. 14	EDTA	0.1	TMAH	2	-		-		△	△	△	△
C. Ex. 15	DTPA	0.1	TMAH	2	-		-		△	O	O	△
C. Ex. 16	NTA	0.1	TMAH	2	-		-		×	×	×	×
C. Ex. 17	HIDA	0.1	TMAH	2	-		-		×	×	×	×
C. Ex. 18	-		PIZ	6	-		-		×	×	×	×

As is clear from Table 2, in each of Examples 15 to 28, the silicon wafer surface has good evaluations for metal impurities. However, in each of Comparative Examples 10 to 18, the silicon wafer surface does not have good evaluations for metal impurities. This is presumed to be due to the fact that the rinsing composition in each of Comparative Examples 10 to 18 does not contain a specific chelating agent.

Examples 29 to 42 and Comparative Examples 19 to 27

In each of Examples 29 to 42 and Comparative Examples 19 to 27, a polishing composition stock solution was prepared by

mixing silicon dioxide, a chelating agent, an alkali compound
and water. The silicon dioxide contained in each polishing
composition stock solution is the same colloidal silica as
that contained in the polishing composition stock solution of
5   Example 1, and each polishing composition stock solution
contains colloidal silica in an amount of 20% by weight. With
regard to the chelating agent and the alkali compound
contained in each polishing composition stock solution, the
kinds and contents thereof are shown in Table 3. In each of
10   Examples 29 to 42, the polishing composition has a pH of from
10 to 12. Each polishing composition stock solution was
diluted to 20 times with ultra pure water to prepare a
polishing composition. Using the polishing composition, the
silicon wafer surface polished under polishing conditions 1
15   was polished under the following polishing conditions 2. In
the following polishing conditions 2, the description of the
same items as those in polishing conditions 1 is omitted.

Polishing conditions 2
20   Object to be polished: 6 inch silicon wafer polished
under the polishing conditions 1 using the polishing
composition of Example 7
         Load: 20.4 kPa
         Polishing pad: Non-woven fabric Suba400 manufactured by
25   Rodel Nitta Corp.
         Polishing time: 10 minutes

         The content of metal impurities that remained on the
silicon wafer surface after the polishing was measured and
30   evaluated in accordance with the method as described in (1),
and the content of metal impurities contained in the inside of
the silicon wafer after the polishing was measured and
evaluated in accordance with the method as described in (2).
Furthermore, the polishing rate was calculated in accordance
35   with the method as described in (3) and evaluated by four

- 22 -

classes, that is, that polishing rate of not lower than 0.6 µm/min is represented by a ◎, a polishing rate of not lower than 0.45 µm/min and lower than 0.6 µm/min is represented by a ○, a polishing rate of not lower than 0.3 µm/min and lower than 0.45 µm/min is represented by a △, and a polishing rate of lower than 0.3 µm/min is represented by a ×. The results are shown in Table 3.

Table 3

| | Chelating agent | | Alkali compound | | | | | | Metal impurities | | | | | | | | Polishing rate |
| | | | | | | | | | silicon wafer surface | | | | silicon wafer inside | | | | |
	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	Fe	Ni	Cu	Ca	Fe	Ni	Cu	Ca	
Ex. 29	DTPPP	0.1	PHA	1.5	-		-		○	○	◎	◎	◎	○	◎	◎	△
Ex. 30	DTPPP	0.1	NCA	1.5	-		-		○	○	◎	◎	◎	○	◎	◎	△
Ex. 31	EDTP	0.1	TMAH	2	-		-		○	○	○	◎	◎	○	○	◎	○
Ex. 32	EDTPP	0.1	TMAH	2	-		-		○	○	○	◎	◎	○	○	◎	○
Ex. 33	DTPP	0.1	TMAH	2	-		-		○	○	◎	◎	◎	○	◎	◎	○
Ex. 34	DTPPP	0.01	TMAH	2	-		-		○	○	○	○	◎	○	○	○	○
Ex. 35	DTPPP	0.1	TMAH	2	-		-		○	○	◎	◎	◎	○	◎	◎	○
Ex. 36	DTPPP	1	TMAH	2	-		-		○	◎	◎	◎	◎	◎	◎	◎	○
Ex. 37	TTHPP	0.1	TMAH	2	-		-		○	◎	◎	◎	◎	◎	◎	◎	○
Ex. 38	TTHP	0.1	TMAH	2	-		-		○	◎	◎	◎	◎	◎	◎	◎	○
Ex. 39	DTPPP	0.1	PIZ	6	-		-		○	○	◎	◎	◎	○	◎	◎	◎
Ex. 40	DTPPP	0.1	PIZ	6	TMAH	1	-		○	○	◎	◎	◎	○	◎	◎	◎
Ex. 41	DTPPP	0.1	PHA	0.5	TMAH	2	-		○	○	◎	◎	◎	○	◎	◎	○
Ex. 42	DTPPP	0.1	PIZ	6	PHA	0.5	TMAH	1	○	○	◎	◎	◎	○	◎	◎	◎
C. Ex. 19	-		EDA	3	-		-		×	×	×	×	×	×	×	×	◎
C. Ex. 20	-		PHA	1.5	-		-		×	×	×	×	×	×	×	×	△
C. Ex. 21	-		NCA	1.5	-		-		×	×	×	×	×	×	×	×	△
C. Ex. 22	-		TMAH	2	-		-		×	×	×	×	×	×	×	×	○
C. Ex. 23	EDTA	0.1	TMAH	2	-		-		△	△	△	△	△	△	△	△	○
C. Ex. 24	DTPA	0.1	TMAH	2	-		-		△	○	○	△	△	○	○	△	○
C. Ex. 25	NTA	0.1	TMAH	2	-		-		×	×	×	×	×	×	×	×	○
C. Ex. 26	HIDA	0.1	TMAH	2	-		-		×	×	×	×	×	×	×	×	○
C. Ex. 27	-		PIZ	6	-		-		×	×	×	×	×	×	×	×	◎

As is clear from Table 3, in each of Examples 29 to 42, both of the silicon wafer surfaces and the silicon wafer

- 23 -

inside have good evaluations for metal impurities and further, in each of Examples 31 to 42, the evaluation of the polishing rate is also good. However, in each of Comparative Examples 19 to 27, both of the silicon wafer surfaces and the silicon

5   wafer inside do not have good evaluations for metal impurities. This is presumed to be due to the fact that the polishing composition in each of Comparative Examples 19 to 27 does not contain a specific chelating agent.

10   Examples 43 to 56 and Comparative Examples 28 to 36
        In each of Examples 43 to 56 and Comparative Examples 28 to 36, a rinsing composition stock solution was prepared by mixing a chelating agent, an alkali compound and water. The kinds and contents of the chelating agent and the alkali

15   compound contained in each rinsing composition stock solution are shown in Table 4. In each of Examples 43 to 56, the rinsing composition stock solution had a pH of from 10 to 12. Each rinsing composition stock solution was diluted to 20 times with ultra pure water to prepare a rinsing composition.

20   Using the rinsing composition, the silicon wafer surface polished under the above-described polishing conditions 2 was rinsed under the following rinsing conditions 2. It should be noted that in the following rinsing conditions 2, the description of the same items as those in polishing conditions

25   1 is omitted.

Rinsing conditions 2
        Object to be rinsed: 6 inch silicon wafer polished in the polishing conditions 2 using the polishing composition of

30   Comparative Example 22
        Polishing pad: Non-woven fabric Suba400 manufactured by Rodel Nitta Corp.

        The content of metal impurities that remained on the

35   silicon wafer surface after the rinsing was measured and

evaluated in accordance with the method as described in (1).
The results are shown in Table 4.

Table 4

	Chelating agent		Alkali compound						Metal impurities			
									silicon wafer surface			
	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	Fe	Ni	Cu	Ca
Ex. 43	DTPPP	0.1	PHA	1.5	-		-		○	○	◎	◎
Ex. 44	DTPPP	0.1	NCA	1.5	-		-		○	○	◎	◎
Ex. 45	EDTP	0.1	TMAH	2	-		-		○	○	○	◎
Ex. 46	EDTPP	0.1	TMAH	2	-		-		○	○	○	◎
Ex. 47	DTPP	0.1	TMAH	2	-		-		○	○	◎	◎
Ex. 48	DTPPP	0.01	TMAH	2	-		-		○	○	○	○
Ex. 49	DTPPP	0.1	TMAH	2	-		-		○	○	◎	◎
Ex. 50	DTPPP	1	TMAH	2	-		-		○	◎	◎	◎
Ex. 51	TTHPP	0.1	TMAH	2	-		-		○	◎	◎	◎
Ex. 52	TTHP	0.1	TMAH	2	-		-		○	◎	◎	◎
Ex. 53	DTPPP	0.1	PIZ	6	-		-		○	○	◎	◎
Ex. 54	DTPPP	0.1	PIZ	6	TMAH	1	-		○	○	◎	◎
Ex. 55	DTPPP	0.1	PHA	0.5	TMAH	2	-		○	○	◎	◎
Ex. 56	DTPPP	0.1	PIZ	6	PHA	0.5	TMAH	1	○	○	◎	◎
C. Ex. 28	-		EDA	3	-		-		×	×	×	×
C. Ex. 29	-		PHA	1.5	-		-		×	×	×	×
C. Ex. 30	-		NCA	1.5	-		-		×	×	×	×
C. Ex. 31	-		TMAH	2	-		-		×	×	×	×
C. Ex. 32	EDTA	0.1	TMAH	2	-		-		△	△	△	△
C. Ex. 33	DTPA	0.1	TMAH	2	-		-		△	○	○	△
C. Ex. 34	NTA	0.1	TMAH	2	-		-		×	×	×	×
C. Ex. 35	HIDA	0.1	TMAH	2	-		-		×	×	×	×
C. Ex. 36	-		PIZ	6	-		-		×	×	×	×

As is clear from Table 4, in each of Examples 43 to 56,
the silicon wafer surface has good evaluations for metal
impurities. However, in each of Comparative Examples 28 to 36,
the silicon wafer surface does not have good evaluations for
metal impurities. This is presumed to be due to the fact that
the rinsing composition in each of Comparative Examples 28 to

- 25 -

36 does not contain a specific chelating agent.

Examples 57 to 72 and Comparative Examples 37 to 44

In each of Examples 57 to 72 and Comparative Examples 37 to 44, a polishing composition stock solution was prepared by mixing either one of additives of hydroxyethyl cellulose (HEC) or polyvinyl alcohol (PVA) in addition to silicon dioxide, a chelating agent, an alkali compound and water. The hydroxyethyl cellulose has an average molecular weight of 1200000, and the polyvinyl alcohol has a degree of saponification of 100%, a degree of polymerization of 1400, and an average molecular weight of 62000. The silicon dioxide contained in each polishing composition stock solution was the same colloidal silica as that contained in the polishing composition stock solution of Example 1, and each polishing composition stock solution contained colloidal silica in an amount of 20% by weight. With regard to the chelating agent, the alkali compound and the additive contained in each polishing composition stock solution, the kinds and contents thereof are shown in Table 5. In each of Examples 57 to 72, the polishing composition had a pH of from 10 to 12. Each polishing composition stock solution was diluted to 200 times with ultra pure water to prepare a polishing composition. Using the polishing composition, the silicon wafer surface polished under the polishing conditions 2 was polished under the following polishing conditions 3. In the following polishing conditions 3, the description of the same items as those in polishing conditions 1 is omitted.

Polishing conditions 3

Object to be polished: 6 inch silicon wafer polished in the polishing conditions 2 using the polishing composition of Example 35

Load: 9.4 kPa

Polishing pad: Surfin000 manufactured by Fujimi

Incorporated

      Feed rate of polishing composition: 500 mL/min (no circulation)

      Polishing time: 8 minutes

5   Temperature of polishing composition: 20°C

      The content of metal impurities that remained on the silicon wafer surface after the polishing was measured and evaluated in accordance with the method as described in (1),

10   and the content of metal impurities contained in the silicon wafer inside after the polishing was measured and evaluated in accordance with the method as described in (2). The results are shown in Table 5.

15

Table 5

	Chelating agent		Alkali compound						Additive		Metal impurities							
											silicon wafer surface				silicon wafer inside			
	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	Fe	Ni	Cu	Ca	Fe	Ni	Cu	Ca
Ex. 57	EDTP	0.1	AM	1	-		-		HEC	0.25	○	○	○	◎	◎	○	○	◎
Ex. 58	EDTPP	0.1	AM	1	-		-		HEC	0.25	○	○	○	◎	◎	○	○	◎
Ex. 59	DTPP	0.1	AM	1	-		-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 60	DTPPP	0.01	AM	1	-		-		HEC	0.25	○	○	○	○	◎	○	○	○
Ex. 61	DTPPP	0.1	AM	1	-		-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 62	DTPPP	1	AM	1	-		-		HEC	0.25	○	◎	◎	◎	◎	◎	◎	◎
Ex. 63	TTHPP	0.1	AM	1	-		-		HEC	0.25	○	◎	◎	◎	◎	◎	◎	◎
Ex. 64	TTHP	0.1	AM	1	-		-		HEC	0.25	○	◎	◎	◎	◎	◎	◎	◎
Ex. 65	DTPPP	0.1	AM	1	-		-		PVA	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 66	DTPPP	0.1	PHA	0.3	-		-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 67	DTPPP	0.1	TMAH	0.5	-		-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 68	DTPPP	0.1	PIZ	0.5	-		-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 69	DTPPP	0.1	AM	0.5	PHA	0.15	-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 70	DTPPP	0.1	AM	0.5	TMAH	0.25	-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 71	DTPPP	0.1	PIZ	0.25	TMAH	0.25	-		HEC	0.25	○	○	◎	◎	◎	○	◎	◎
Ex. 72	DTPPP	0.1	PHA	0.1	TMAH	0.2	PIZ	0.2	HEC	0.25	○	○	◎	◎	◎	○	◎	◎
C. Ex. 37	-		AM	1	-		-		HEC	0.25	×	×	×	×	×	×	×	×
C. Ex. 38	EDTA	0.1	AM	1	-		-		HEC	0.25	△	△	△	△	△	△	△	△
C. Ex. 39	DTPA	0.1	AM	1	-		-		HEC	0.25	△	○	○	△	△	○	○	△
C. Ex. 40	NTA	0.1	AM	1	-		-		HEC	0.25	×	×	×	×	×	×	×	×
C. Ex. 41	HIDA	0.1	AM	1	-		-		HEC	0.25	×	×	×	×	×	×	×	×
C. Ex. 42	-		PHA	0.3	-		-		HEC	0.25	×	×	×	×	×	×	×	×
C. Ex. 43	-		TMAH	0.5	-		-		HEC	0.25	×	×	×	×	×	×	×	×
C. Ex. 44	-		PIZ	0.5	-		-		HEC	0.25	×	×	×	×	×	×	×	×

In Table 5, AM represents a 29% by weight ammonia aqueous solution. As is clear from Table 5, in each of Examples 57 to 72, both the silicon wafer surface and the silicon wafer inside have good evaluations for metal impurities. However, in each of Comparative Examples 37 to 44, both the silicon wafer surface and the silicon wafer inside do not have good evaluations for metal impurities. This is presumed to be due to the fact that the polishing composition in each of

- 28 -

Comparative Examples 37 to 44 does not contain a specific chelating agent.

Examples 73 to 88 and Comparative Examples 45 to 52

In each of Examples 73 to 88 and Comparative Examples 45 to 52, a rinsing composition stock solution was prepared by mixing either one of additives of HEC or PVA in addition to a chelating agent, an alkali compound and water. The hydroxyethyl cellulose had an average molecular weight of 1200000, and the polyvinyl alcohol had a degree of saponification of 100%, a degree of polymerization of 1400, and an average molecular weight of 62000. With regard to the chelating agent, the alkali compound and the additive contained in each rinsing composition stock solution, the kinds and contents thereof are shown in Table 6. In each of Examples 73 to 88, the rinsing composition stock solution had a pH of from 10 to 12. Each rinsing composition stock solution was diluted to 20 times with ultra pure water to prepare a rinsing composition. Using the rinsing composition, the silicon wafer surface polished under the above-described polishing conditions 3 was rinsed under the following rinsing conditions 3. In the following rinsing conditions 3, the description of the same items as those in rinsing conditions 1 is omitted.

Rinsing conditions 3

Object to be rinsed: 6 inch silicon wafer polished under polishing conditions 3 using the polishing composition of Comparative Example 43

Polishing pad: Surfin000 manufactured by Fujimi Incorporated

Feed rate of rinsing composition: 2000 mL/min (no circulation)

Rinsing time: 30 seconds

The content of metal impurities on the silicon wafer surface after the rinsing was measured and evaluated in accordance with the method as described in (1). The results are shown in Table 6.

5

Table 6

	Chelating agent		Alkali compound						Additive		Metal impurities			
											silicon wafer surface			
	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	kind	content (weight %)	Fe	Ni	Cu	Ca
Ex. 73	EDTP	0.1	AM	1	-		-		HEC	0.25	O	O	O	◎
Ex. 74	EDTPP	0.1	AM	1	-		-		HEC	0.25	O	O	O	◎
Ex. 75	DTPP	0.1	AM	1	-		-		HEC	0.25	O	O	◎	◎
Ex. 76	DTPPP	0.01	AM	1	-		-		HEC	0.25	O	O	O	O
Ex. 77	DTPPP	0.1	AM	1	-		-		HEC	0.25	O	O	◎	◎
Ex. 78	DTPPP	1	AM	1	-		-		HEC	0.25	O	◎	◎	◎
Ex. 79	TTHPP	0.1	AM	1	-		-		HEC	0.25	O	◎	◎	◎
Ex. 80	TTHP	0.1	AM	1	-		-		HEC	0.25	O	◎	◎	◎
Ex. 81	DTPPP	0.1	AM	1	-		-		PVA	0.25	O	O	◎	◎
Ex. 82	DTPPP	0.1	PHA	0.3	-		-		HEC	0.25	O	O	◎	◎
Ex. 83	DTPPP	0.1	TMAH	0.5	-		-		HEC	0.25	O	O	◎	◎
Ex. 84	DTPPP	0.1	PIZ	0.5	-		-		HEC	0.25	O	O	◎	◎
Ex. 85	DTPPP	0.1	AM	0.5	PHA	0.15	-		HEC	0.25	O	O	◎	◎
Ex. 86	DTPPP	0.1	AM	0.5	TMAH	0.25	-		HEC	0.25	O	O	◎	◎
Ex. 87	DTPPP	0.1	PIZ	0.25	TMAH	0.25	-		HEC	0.25	O	O	◎	◎
Ex. 88	DTPPP	0.1	PHA	0.1	TMAH	0.2	PIZ	0.2	HEC	0.25	O	O	◎	◎
C. Ex. 45	-		AM	1	-		-		HEC	0.25	×	×	×	×
C. Ex. 46	EDTA	0.1	AM	1	-		-		HEC	0.25	△	△	△	△
C. Ex. 47	DTPA	0.1	AM	1	-		-		HEC	0.25	△	O	O	△
C. Ex. 48	NTA	0.1	AM	1	-		-		HEC	0.25	×	×	×	×
C. Ex. 49	HIDA	0.1	AM	1	-		-		HEC	0.25	×	×	×	×
C. Ex. 50	-		PHA	0.3	-		-		HEC	0.25	×	×	×	×
C. Ex. 51	-		TMAH	0.5	-		-		HEC	0.25	×	×	×	×
C. Ex. 52	-		PIZ	0.5	-		-		HEC	0.25	×	×	×	×

In Table 6, AM represents a 29% by weight ammonia aqueous solution. As is clear from Table 6, in each of Examples 73 to
10 88, the silicon wafer surface has good evaluations for metal impurities. However, in each of Comparative Examples 45 to 52,

the silicon wafer surface does not have good evaluations for
metal impurities. This is presumed to be due to the fact that
the polishing composition in each of Comparative Examples 45
to 52 does not contain a specific chelating agent.

5